



TENSILE STRENGTH TEST ON PVC FABRIC (TWO LAYERS) WITH PLASTGrommet Ø12mm.


ALL TESTS HAVE BEEN MADE By EPSA (University of Valencia)

TEST DATA


Date:	24/07/2007
Machine Charging Cell:	5kN
Charging Rate:	0,1 kN/s
Eyelet:	Test carried on a single eyelet

MAIN RESULTS

Test:	Tension over strap(bottom) and tension over fabric(top)
Maximum breaking force:	135,12 Kgf (fracture of the fabric)



PICTURE 1
SAMPLES BEFORE THE TEST



PICTURE 2
SAMPLE AFTER TEST



PICTURE 3
CLOSED-UP OF TEST

