



## Resistance to chemicals and UV

### **TESTS CARRIED OUT ON PLASTGrommet PRODUCTS**

TEST	DES	SCR	IPT		N
ILJI	$\nu_{\rm L}$	ンしい		$\sim$	ıv

#### **STANDARD**

#### **RESULTS**

CORROSION IN AMBIENCE OF SALINE NEUTRAL FOG	ASTM B-117:85	NO CHANGES IN THE SAMPLES		
EXPOSURE TO SUN LIGHT (XENON TEST)	UNE EN ISO 4892-2:2000 250 HOURS (+/- 3,5 YEARS)	NO CHANGE IN COLOUR		
FASTNESS TO ACIDS	UNE-EN ISO-105 E05/98	TARTARIC ACID ACETIC ACID SULFURIC ACID 5 5 5		
FASTNESS TO CHLORINATED WATER (SWIMMING-POOL WATER)	UNE-EN ISO 105-E03:1997	5		
FASTNESS TO SALFUMAN	AITEX TEST	5		
FASTNESS TO ALCOHOL	AITEX TEST	5		
FASTNESS TO CITRUS	AITEX TEST	5		
FASTNESS TO DRY CLEANING	UNEEN ISO 105-D01:1996	CHANGE IN COLOUR STAINING IN THE SOLVENT 5		
FASTNESS TO BLEACHING: HYPOCLORITE	UNE-EN ISO 20105-N01:1996	5		
DETERMINATION OF pH VALUE	EN 3071:2006	7.39		
FASTNESS TO ALKALIS (SODIUM CARBONATE)	UNE-EN ISO-105 E06/1989	5		
FASTNESS TO PHOSPORIC ACID	AITEX TEST	5		
CLIMATIC AGING (Samples were subjected to accelerated aging process during 48 hours to -40 °C.)	AITEX TEST	LOOSE EYELETS EYELETS SET EYELETS SET ON FABRIC  No changes, it is possible to set them on fabric  No changes  No changes  No changes		

**RAW MATERIAL** 

**UL FLAMMABILITY CLASSIFICATION** DEFLECTION TEMPERATURE @ 0.455 Mpa (4,6 kgf/cm²) DEFLECTION TEMPERATURE @ 1.82 Mpa (18,55 kgf/cm²) THERMOPLASTIC POLYMER

94 - V-2 73 °C 65 °C

MEANING OF FASTNESS APPRAISAL EVALUETED WITH ESCALE OF GREYS

2-1 POOR BEHAVIOUR

CHANGE IN COLOUR: 5 GOOD BEHAVIOUR STAINING: 5 VERY GOOD-EXCELLENT 43 FAIR BEHAVIOUR 4 GOOD 3 FAIR 2 POOR

1 VERY POOR

# **CLEAR EYELETS**

- · Crystal clear, they simply disappear on the banners.
- Easy to use.
- · Do not rust, perfect for outdoors.
- · Environmentally friendly, perfect for green printers using Latex inks and nonharmful medias.
- · Can be recycled with PP and HDPE medias.
- PVC free.
- Free of heavy metals (lead, cadmium and mercury).
- Food grade (FDA and EU).





**SIGNGEER.COM** 0800 5 999 059